EN 12164, Copper and copper alloys — Rod for free machining purposes																
Designations			Diameter			Width across - flats			Tensile Strength	0,2% proof strength		Elongation			Hardness	
Material		Material Condition	mm			mm			Rm (Mpa)	Rp 0,2 (Mpa)		A 100 (%)	A 11,3 (%)	A (%)	HBW	
Number	Symbol		from	over	up to and including	from	over	up to and including	min.	min.	max.	min.	min.	min.	min.	max.
CW601N	CuZn35Pb2	M	All			All			As manufactured							
		R340	10	-	80	10	-	60	340	-	280	-	-	20	-	-
		H070	10	-	80	10	-	60	-	-	-	-	-	-	70	120
		R400	2	-	25	2	-	20	400	200	-	4	8	12	-	-
		H100	2	-	25	2	-	20	-	-	-	-	-	-	100	140
		R480	2	-	14	2	-	10	480	350	-	3	5	8	-	-
		H125	2	-	14	2	-	10	-	-	-	-	-	-	125	-

EN 12166, Copper and copper alloys — Wire for general purposes													
Designations			Diameter		Tensile Strength	0,2% proof strength		Elongation			Hardness	
Material		Material Condition	mm		Rm (Mpa)	Rp 0,2 (Mpa)		A 100 (%)	A 11,3 (%)	A (%)	HV	
Number	Symbol		from	up to and including	min.	min.	max.	min.	min.	min.	min.	max.
CW601N	CuZn35Pb2	M	All		As manufactured							
		R340	0,5	20	340	-	280	10	15	20	-	-
		H080	1,5	20	-	-	-	-	-	-	80	130
		R400	0,5	14	400	200	-	4	8	12	-	-
		H100	1,5	14	-	-	-	-	-	-	100	150
		R480	0,5	8	480	350	-	2	5	-	-	-
		H135	1,5	8	-	-	-	-	-	-	135	-